

Storage of varnished, permanently sticky playing cards

Maria Krämer
Eva Hummert
Irene Brückle

Studiengang
Konservierung und Restaurierung
von Kunstwerken auf Papier,
Archiv- und Bibliotheksgut

STAATLICHE
AKADEMIE DER
BILDENDEN KÜNSTE
STUTT GART

Prior to the storage project discussed here, this set of 20th-century Chinese domino playing cards had undergone treatment to separate them. The cards had been blocked due to a coating consisting of shellac with protein and oil components that caused the card surfaces to be permanently sticky. The individual cards were stuck together as a result. The treatment to separate them involved developing a cold temperature application method to cool the varnish below its glass transition temperature,




Fig. 2. Box with trays, opened (a) and closed (b, schematic cross section)



Fig. 1. Playing cards after separation



Fig. 3. Box with opened flap

which made the coating temporarily brittle and the cards separable (fig. 1).

In order to prevent future re-adhesion of the cards, an archival box was custom-designed. The storage box, manufactured by Klug-Conservation, is made of archival-quality corrugated board and consists of the base of the box, a lid and three inserted trays (fig. 2) that are accessible by lowering the flap (fig. 3). Each tray is




Fig. 4. Concertina-folded support inside tray (schematic cross section)

furnished with concertina-folded supports, which are made from strips of archival board and silicone release paper. The release paper is sewn onto the board material with book binding thread and adhered to the tray at the ends (fig. 4). Silicone release paper (silicone-coated paper with a surface pH of 6.0) was chosen as the contacting support material because it proved to have the best separating properties, which is the most important factor when storing the sticky cards. The slightly acidic pH value is unlikely to have any adverse effect on the cards, which are coated with varnish. Each card rests in a separate compartment of this box and can be viewed without being touched or removed (fig. 5). The concertina-supports are fixed on the tablets only at their opposite ends, so that each individual compartment can be widened. This makes it easier to access the cards.



Fig. 5. Accessing a playing card in its compartment

Materials:

custom-made archival box (Klug-Conservation, Immenstadt): corrugated board, MW 1.6mm. Folded supporting: Archival board 048, light-grey, 330g/m² (Klug-Conservation), Silicone Release Paper (Talas, New York); Sewing: book binding thread, flax, Nr. 60 (Leo's Nachfolger GmbH, Stuttgart); adhesive: gelatine, food-grade (Merck KGaA)

Literature

E. Carrlee: Does Low-Temperature Pest Management Cause Damage? *Journal of the American Institute of Conservation* 42, 2 (2003): 144–161.

M. Krämer, E. Hummert, I. Brückle: Die Trennung gefirnisster Karten eines chinesischen Dominospiels, *Zeitschrift für Kunsttechnologie und Konservierung* 30 (2016): in print. (The article is based on the bachelor's thesis by Maria Krämer, student of the paper conservation course, State academy of Arts, Stuttgart, 2013.

D. Müller: Prüfung von Zwischenlagematerialien zur Lagerung des Nachlasses von Ernst Jünger am Deutschen Literaturarchiv Marbach, 2015, unpublished term paper, paper conservation programme, Stuttgart.